

AMENDMENTS TO THE ABSTRACT

Please substitute the following paragraph(s) for the abstract now appearing in the currently filed specification:

Cast part with high creep resistance, made of an alloy with a composition comprising (% by weight):

Si: 5 - 11

Fe < 0.6

Mg: 0.15 - 0.6

Cu: 0.3 - 1.5

Ti: 0.05 - 0.25

Zr: 0.05 - 0.25

Mn < 0.4

Zn < 0.3

Ni < 0.4

other elements < 0.10 each and 0.30 total, remainder aluminium.